

SBR-1502 Polymer Data

0DR 1002 1019	mer Dutu				
Polymerization System		Cold emuls	Cold emulsion Polymerization		
			Mixed acid soap		
			Non-Staining, Non-discoloring		
\mathcal{O}			Acid		
Characteristics		Bright colored stock with excellent color stability.			
		Improved abrasion resistance, flexibility, where excellent physical properties and non-staining antioxidant are			
		required.			
Application		Tires (especially white sidewall), shoe soles and heels,			
		sporting goods, floor coverings, industrial goods (especially light colored goods) and miscellaneous			
		items			
		Specificat	tion Values		
POLYMER PROP	PERTIES	<u>minimum</u> .	<u>maximum</u>	Test Method	
Bound Styrene	(%)	22.5	24.5	ASTM D-5775	
Volatile Matter	(%)		0.75	ASTM D-5668	
Ash	(%)		0.75	ASTM D-5667	
Organic Acid	(%)	4.75	7.00	ASTM D-5774	
Soap	(%)		0.50	ASTM D-5774	
Mooney Viscosity	$V, ML_{1+4}, 100$	°C* 46	58	ASTM D-1646	
* Massed sample	<u>,</u>				
COMPOUND PR	OPERTIES(Test Recipe AST	M D-3185; Cure	@ 145°C)	
Tensile Strength	35' (kg/	cm^2) 230		ASTM D-412	
Elongation	35' (%)	330		ASTM D-412	
300% Modulus	25' (kg/	cm^2) 130	170	ASTM D-412	
	35' (kg/	cm^2) 160	200	ASTM D-412	
	50' (kg/	cm^2) 175	215	ASTM D-412	
Test Recipe, AST	<u>'M D-3185</u>	Parts			
Taipol SBR-150)2	100.00			
Zinc oxide	3.00				
Stearic acid	1.00				
Sulfur		1.75			
HAF black(IRB#9)		50.00			
TBBS		1.00			
Total		156.75			

本資料為台橡股份有限公司之機密及專有之財產,非經書面許可,不准透露或使用本資料,亦不准複印、複製或轉變成任何其他形式使用。The information contained herein is confidential and an exclusive property of TSRC corporation and shall not be distributed, or disclosed in whole or in part without prior permission of TSRC corporation.



Limited warranty

There are no warranties which extend beyond the product description herein, and seller makes no warranty, express or implied, of fitness for particular use, merchantability or otherwise with respect to product, whether used singly or in combination with other substances or in any process, except that product sold hereunder shall conform to seller's standard sales specifications as of the date of the shipment. Without limiting the foregoing, seller does not recommend or endorse the use of product(s) in any medical application and specifically disclaims any representation or warranty, express or implied, of suitability or fitness for use or otherwise, with respect to product(s)' use in any medical application. Buyer represents and warrants that no product(s) purchased hereunder will be used in or resold into any commercial or developmental manner in connection with medical applications without seller's prior express written acknowledgement, further, buyer agrees that it will make no representations, express or implied, to any person to the effect that seller recommends or endorses the use of product(s) purchased hereunder in any medical application.