



SBR-1778 Polymer Data

Polymerization System	-- Cold emulsion Polymerization
Emulsifier	-- Mixed acid soap
Stabilizer	-- Non-Staining, non-discoloring
Coagulant	-- Acid
Extender	-- Semi-paraffinic oil, 37.5 parts
Characteristics	-- Light colored and excellent processing properties ,.
Application	-- Hoses, sports goods, shoe soles, conveyor belt, tire and other industrial products.

Specification Values

<u>POLYMER PROPERTIES</u>		<u>minimum.</u>	<u>maximum</u>	<u>Test Method</u>
Bound Styrene	(%)	22.5	24.5	ASTM D-5775
Volatile Matter	(%)	-----	0.75	ASTM D-5668
Ash	(%)	-----	1.00	ASTM D-5667
Organic Acid	(%)	3.90	5.70	ASTM D-5774
Soap	(%)	-----	0.50	ASTM D-5774
Mooney Viscosity, ML ₁₊₄ , 100°C *		40	54	ASTM D-1646

* Massed sample

COMPOUND PROPERTIES(Test Recipe ASTM D-3185; Cure @ 145°C)

Tensile Strength	35° (kg/cm ²)	160	---	ASTM D-412
Elongation	35° (%)	380	---	ASTM D-412
300% Modulus	25° (kg/cm ²)	65	105	ASTM D-412
	35° (kg/cm ²)	90	130	ASTM D-412
	50° (kg/cm ²)	110	150	ASTM D-412

Test Recipe, ASTM D-3185 **Parts**

Taipol SBR-1778	137.50
Zinc oxide	3.00
Stearic acid	1.00
Sulfur	1.75
HAF black(IRB#8)	68.75
<u>TBBS</u>	<u>1.38</u>
Total	213.38



台橡股份有限公司
TSRC CORPORATION

Limited warranty

There are no warranties which extend beyond the product description herein, and seller makes no warranty, express or implied, of fitness for particular use, merchantability or otherwise with respect to product, whether used singly or in combination with other substances or in any process, except that product sold hereunder shall conform to seller's standard sales specifications as of the date of the shipment. Without limiting the foregoing, seller does not recommend or endorse the use of product(s) in any medical application and specifically disclaims any representation or warranty, express or implied, of suitability or fitness for use or otherwise, with respect to product(s)' use in any medical application. Buyer represents and warrants that no product(s) purchased hereunder will be used in or resold into any commercial or developmental manner in connection with medical applications without seller's prior express written acknowledgement, further, buyer agrees that it will make no representations, express or implied, to any person to the effect that seller recommends or endorses the use of product(s) purchased hereunder in any medical application.

台橡股份有限公司

總公司：台北市106敦化南路二段95號18樓

高雄廠：高雄市815大社區興工路2號

岡山廠：高雄市820岡山區本工一路39號

電話：+886(2)3701 6000

電話：+886(7)351 3811

電話：+886(7)623 3005

傳真：+886(2)3701 6868

傳真：+886(7)351 4705

傳真：+886(7)622 5481

TSRC Corporation

Head office 18F., 95, Sec. 2, Dunhua S. Rd., Taipei City 106, Taiwan R.O.C.

Kaohsiung Factory No.2, Singgong Rd., Dashe Dist., Kaohsiung City 815, Taiwan R.O.C.

Gangshan Factory No.39, Bengong 1st Rd., Gangshan Dist., Kaohsiung City 820, Taiwan R.O.C.

Tel : +886(2)3701 6000 Fax : +886(2)3701 6868

Tel : +886(7)351 3811 Fax : +886(7)351 4705

Tel : +886(7)623 3005 Fax : +886(7)622 5481