

TECHNICAL PRODUCT DATA TSR 10 RUBBER

- Chemical characterization: Natural Rubber (NR) consisting essentially of cis-1,4-Polyisoprene with small amounts of non-rubber constituents (Proteins, Lipids).
- TSR 10 is prepared from clean and fresher field-grade material (coagulum) or from unsmoked sheets.
- Change in physical state 10 - - 35 °C after long periods of storage.
- Combustion with restricted access of air can result in the evolution of carbon monoxide gas.
- Packing in wooden pallet crates or shrink-wrapped on pallet bases.

	Specifications	Test method
Dirt	Max. 0.08 %	ISO 249
Ash	Max. 0.75 %	ISO 247
Volatile Matter	Max. 0.80 %	ISO 248
N2	Max. 0.60 %	ISO 1656
P₀	Min. 30	ISO 2007
P.R.I.	Min. 50	ISO 2930