

TECHNICAL PRODUCT DATA **TSR 10CV 60 RUBBER**

- Chemical characterization: natural rubber (NR) consisting essentially of cis-1,4-Polyisoprene with small amounts of non-rubber constituents (Proteins, Lipids).
- TSR 10CV 60 is prepared from clean and fresh field-grade material (coagulum) or from unsmoked sheets.
- TSR 10CV 60 is a viscosity-stabilised field grade, produced under controlled circumstances, being under high consumer demand.
- Change in physical state 10 - 35 °C after long periods of storage.
- Combustion with restricted access of air can result in the evolution of carbon monoxide gas.
- Packing in wooden palletcrates or shrinkwrapped on pallet bases..

	Specifications	Test Method
Dirt	Max. 0.10 %	ISO 249
Ash	Max. 0,75 %	ISO 247
Volatile Matter	Max. 0.80 %	ISO 248
N2	Max. 0.60 %	ISO 1656
P₀	--	
P.R.I.	Min. 50	ISO 2930
Mooney Viscosity (*) ML (1'+4')100°C	60 +7,-5	ISO 289

(*) The Mooney Viscosity is not of specification status.

