

## TECHNICAL PRODUCT DATA      **TSR CV 60 RUBBER**

- Chemical characterization: natural rubber (NR) consisting essentially of cis-1,4-Polyisoprene with small amounts of non-rubber constituents (Proteins, Lipids).
- TSR CV 60 is produced from high quality wholefield latex, bulked and acid coagulated under controlled conditions.
- TSR CV 60 rubber has a low ash and dirt content.
- Change in physical state 10 - 35 °C after long periods of storage.
- Combustion with restricted access of air can result in the evolution of carbon monoxide gas.

	Specifications	Test method
<b>Dirt</b>	Max. 0.05 %	ISO 249
<b>Ash</b>	Max. 0.60 %	ISO 247
<b>Volatile Matter</b>	Max. 0.80 %	ISO 248
<b>N2</b>	Max. 0.60 %	ISO 1656
<b>P<sub>0</sub></b>	--	
<b>P.R.I.</b>	Min. 60	ISO 2930
<b>Mooney Viscosity ML (1'+4')100°C.</b>	60 ±5	ISO 289



ASSOCIATE MEMBER



ASSOCIATE MEMBER